

Unilin Flooring Polska Sp. z o.o.
Powstancow Śląskich 54
42700 LUBLINIEC
Poland

Your notice of
19-11-2024

Your reference
SP2L2001941548

Date
02-01-2025

Analysis Report 24.06214.01

Required tests :


EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2423231	VA23 ADRIATICO 70	19-11-2024



Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T2423231 - VA23 ADRIATICO 70

Information given by the client

Product standard	EN 13501-1 (2019)
Floor covering type	Heterogeneous poly(vinyl chloride) flooring on foam
EN product standard	EN ISO 11638
FR treated	no
Mass	2050 g/m ²
Thickness	2.0 mm

Notified body No: 0493



Reference: T2423231 - VA23 ADRIATICO 70

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test


Date of ending the test 09-12-2024
Standard used EN ISO 11925-2 (2020)
Product standard EN 13501-1 (2019)

Floor covering

Deviation from the standard -
Conditioning 23°C, relative humidity 50%
Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Weight (g/m²) 1845
Dimension of the specimens 250 mm x 90 mm x 2 mm
Substrate Fibre cement board - density (1800 ± 200) kg/m³
Mounting Loose-laid
Specimens have not been cleaned



Flame application time (s)

15

Flame application

Surface - front

	Length			Width		
	1	2	3	4	5	6
Ignition	no	no	no	no	no	no
Time to reach 150 mm mark (s)	*	*	*	*	*	*
Additional observations						
Molten debris within 20 s after flame application	no	no	no	no	no	no
Hole formed within 20 s after flame application	no	no	no	no	no	no

* = time to reach the mark > 20 s or mark not reached


Criteria Floorcoverings

time to reach the mark:

- > 20 s : Class Efl
- \leq 20 s : Class Ffl

Classification

Class Efl



Reference: T2423231 - VA23 ADRIATICO 70


Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	23-12-2024
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2019)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Particle board - density (680 ± 50) kg/m ³
Mounting	Stuck down with UZIN UZ 57 / Unipro - low emission, solvent-free dispersion adhesive – "EC1 very low emission"
Specimens have not been cleaned	



Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux *
	10 min	20 min	30 min		
Length					
#1	21	21	21	13 min 53 s	9.4
Width					
#1	26	26	26	14 min 45 s	8.4
#2	20	20	20	13 min 22 s	9.5
#3	20	26	28	25 min 46 s	7.9
Average					8.6


* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux $\geq 8,0 \text{ kW/m}^2$
C _{fl}	E _{fl}	heat flux $\geq 4,5 \text{ kW/m}^2$
D _{fl}	E _{fl}	heat flux $\geq 3,0 \text{ kW/m}^2$

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Length		
#1	81	201
Width		
#1	83	176
#2	72	191
#3	77	253
Average		207

Additional classification in accordance with EN 13501-1 (2019)	
smoke production $\leq 750\%\text{.min}$	s1
smoke production $> 750\%\text{.min}$	s2



Reaction to fire classification : Bfl / s1

*Glued on a combustible substrate**

** End use substrates of wood and of classes A1 and A2-s1,d0 (EN 13238:2010 § 5.2.3)*

Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of performance by the manufacturer within the context of system 3 of assessment and verification of constancy of performance and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”